



DEPARTMENT OF REGULATORY AND ECONOMIC RESOURCES (RER)
BOARD AND CODE ADMINISTRATION DIVISION

NOTICE OF ACCEPTANCE (NOA)

**MIAMI-DADE COUNTY
PRODUCT CONTROL SECTION**

11805 SW 26 Street, Room 208
Miami, Florida 33175-2474
T (786)315-2590 F (786) 31525-99

www.miamidade.gov/economy

**Seaman Corporation
1000 Venture Boulevard
Wooster, OH 44691**

SCOPE:

This NOA is being issued under the applicable rules and regulations governing the use of construction materials. The documentation submitted has been reviewed and accepted by Miami-Dade County RER - Product Control Section to be used in Miami Dade County and other areas where allowed by the Authority Having Jurisdiction (AHJ).

This NOA shall not be valid after the expiration date stated below. The Miami-Dade County Product Control Section (In Miami Dade County) and/or the AHJ (in areas other than Miami Dade County) reserve the right to have this product or material tested for quality assurance purposes. If this product or material fails to perform in the accepted manner, the manufacturer will incur the expense of such testing and the AHJ may immediately revoke, modify, or suspend the use of such product or material within their jurisdiction. RER reserves the right to revoke this acceptance, if it is determined by Miami-Dade County Product Control Section that this product or material fails to meet the requirements of the applicable building code.

This product is approved as described herein, and has been designed to comply with the Florida Building Code including the High Velocity Hurricane Zone of the Florida Building Code.

DESCRIPTION: FiberTite Single Ply Roof Systems over Cementitious Wood Fiber Decks.

LABELING: Each unit shall bear a permanent label with the manufacturer's name or logo, city, state and following statement: "Miami-Dade County Product Control Approved", unless otherwise noted herein.

RENEWAL of this NOA shall be considered after a renewal application has been filed and there has been no change in the applicable building code negatively affecting the performance of this product.

TERMINATION of this NOA will occur after the expiration date or if there has been a revision or change in the materials, use, and/or manufacture of the product or process. Misuse of this NOA as an endorsement of any product, for sales, advertising or any other purposes shall automatically terminate this NOA. Failure to comply with any section of this NOA shall be cause for termination and removal of NOA.

ADVERTISEMENT: The NOA number preceded by the words Miami-Dade County, Florida, and followed by the expiration date may be displayed in advertising literature. If any portion of the NOA is displayed, then it shall be done in its entirety.

INSPECTION: A copy of this entire NOA shall be provided to the user by the manufacturer or its distributors and shall be available for inspection at the job site at the request of the Building Official.

This revises NOA # 12-1019.33 and consists of pages 1 through 7.
The submitted documentation was reviewed by Alex Tigera.



**NOA No.: 15-1026.06
Expiration Date: 01/05/21
Approval Date: 12/24/15
Page 1 of 7**

ROOFING SYSTEM APPROVAL

<u>Category:</u>	Roofing
<u>Sub-Category:</u>	Single Ply
<u>Material:</u>	KEE
<u>Deck Type:</u>	Cementitious Wood Fiber
<u>Maximum Design Pressure</u>	-45 psf

TRADE NAMES OF PRODUCTS MANUFACTURED OR LABELED BY APPLICANT:

TABLE 1

<u>Product</u>	<u>Dimensions</u>	<u>Test Specification</u>	<u>Product Description</u>
FiberTite	Various	ASTM D 6754	KEE, polyester reinforced, single ply membrane
FiberTite-XT	Various	ASTM D 6754	KEE, polyester reinforced, single ply membrane
FiberTite-SM	Various	ASTM D 6754	KEE, polyester reinforced, single ply membrane
FiberTite-XTreme	Various	ASTM D 6754	KEE, polyester reinforced, single ply membrane
Style 80, Style 80-M	Various	ASTM D 6754	KEE, polyester reinforced, single ply membrane
FiberTite FB	54" x 100'	ASTM D 6754	KEE, fleece-backed, single ply membrane
FiberTite-XT FB	Various	ASTM D 6754	KEE, fleece-backed, polyester reinforced, single ply membrane
FiberTite-SM FB	Various	ASTM D 6754	KEE, fleece-backed, polyester reinforced, single ply membrane
Style 80 FB, Style 80-M FB	Various	ASTM D 6754	KEE, fleece-backed, polyester reinforced, single ply membrane
FTR Non-Reinforced	0.060" x 54" x 24'	ASTM D 6754	KEE flashing accessory
FTR Cones	1" to 8"	ASTM D 6754	Premolded "KEE" pipe flashing
FTR Corners	2' x 2'	ASTM D 6754	Premolded "KEE" corner flashing (4 per unit)
FiberClad	48" x 120"	N/A	Polymeric coated G-90 galvanized steel or stainless steel
Tuff Trac	5/32" x 36" x 40' 1/4" x 24" x 48"	N/A	Vinyl walk way; Vinyl protection pad



APPROVED INSULATIONS:**TABLE 2**

<u>Product Name</u>	<u>Product Description</u>	<u>Manufacturer (With Current NOA)</u>
FTR-Value, FTR-Value H	Isocyanurate Insulation	Seaman Corporation
ACFoam Composite	Isocyanurate Insulation with perlite facer	Atlas Roofing Corporation
EnergyGuard Composite	Isocyanurate foam insulation with high density fiberboard or perlite insulation.	GAF Materials Corporation
DensDeck	Silicon treated gypsum	Georgia-Pacific Gypsum LLC
Wood Fiberboard	Regular Wood Fiber insulation board.	Generic
Perlite Insulation Board	Perlite Insulation	Generic
H-Shield	Isocyanurate Insulation	Hunter Panels, LLC
ENRGY 3	Isocyanurate Insulation	Johns Manville Corporation
Fesco Foam	Polyisocyanurate Insulation with perlite facer	Johns Manville Corporation
Multi-Max FA-3	Polyisocyanurate foam insulation	Rmax Operating, LLC
Thermarroof Composite-3	Polyisocyanurate/perlite composite insulation.	Rmax Operating, LLC

APPROVED FASTENERS:**TABLE 3**

<u>Fastener Number</u>	<u>Product Name</u>	<u>Product Description</u>	<u>Dimensions</u>	<u>Manufacturer (With Current NOA)</u>
1.	Polymer GypTec	Fastener for cementitious and gypsum decks	Various	OMG, Inc.
2.	Polymer GypTec Insulation Plate	Round Galvalume AZ55 plate	3" round	OMG, Inc



EVIDENCE SUBMITTED:

<u>Test Agency/Identifier</u>	<u>Name</u>	<u>Report</u>	<u>Date</u>
Factory Mutual Research Corp.	FM 4470	1Z2A5.AM	01/12/96
	FM 4470	Z3A8.AM	08/13/97
	FM 4470	3002471	10/06/99
	FM 4470	3013068	09/23/03
Underwriters Laboratories	UL790	98NK12510	08/11/98
	UL790	98NK17212	08/21/98
Exterior Research & Design, LLC	TAS 114	4015.10.96-1-R1	07/20/10
	TAS 114	4006.07.97-1-R1	07/15/10
	TAS 114	4006.08.00-1-R1	10/18/05
	TAS 117 & ASTM D6862	C850SC.11.07-R1	08/07/09
Trinity ERD	ASTM D 6754	S47410.12.14	12/15/14
PRI Construction Materials Technologies LLC	ASTM D 3747	HGC-142-02-03	02/09/12

APPROVED ASSEMBLIES

Membrane Type:	Single Ply, KEE
Deck Type 5I:	Cementitious Wood Fiber, Insulated
Deck Description:	Cementitious wood fiber
System Type D:	Membrane mechanically attached over preliminary fastened insulation.

All General and System Limitations apply. Roof accessories not listed in Table 1 of this NOA are not approved and shall not be installed unless said accessories demonstrate compliance with prescriptive Florida Building Code requirements and are field fabricated utilizing the approved membranes listed in Table 1.

One or more layers of any of the following insulations:

<u>Insulation Layer</u>	<u>Insulation Fasteners (Table 3)</u>	<u>Fastener Density/ft²</u>
FTR-Value, Multi-Max FA-3, ENRGY 3, ACFoam Composite, EnergyGuard Composite, Thermaroom Composite-3, Fesco Foam, H-Shield, FTR-Value H Minimum 1.5" thick	N/A	N/A
Approved Wood Fiberboard Minimum ½" thick	N/A	N/A
Approved Perlite Minimum ¾" thick	N/A	N/A

Note: All insulation shall have preliminary attachment, prior to the installation of the roofing membrane at a minimum application rate of two fasteners per board for insulation boards having no dimension greater than 4 ft., and four fasteners for any insulation board having no dimension greater than 8 ft.

Vapor Barrier: (Optional)	Any UL or FM approved vapor barrier applied to the roof deck or over a base layer of insulation.
Fire Barrier: (Optional)	¼" or ½" DensDeck applied to the base or top insulation layer.
Membrane:	FiberTite, FiberTite-XT, FiberTite-SM, FiberTite-XTreme, Style 80 or Style 80-M roof cover attached through the preliminary fastened insulation to the deck as specified below:
Fastening:	Fasten with Polymer GypTec fasteners and plates spaced 6" o.c. through the fastening tabs spaced 51" o.c. Laps are sealed with 1.5-inch heat weld.
Maximum Design Pressure:	-45 psf (See General Limitation #9)



Membrane Type: Single Ply, KEE
Deck Type 5: Cementitious Wood Fiber, Non-Insulated
Deck Description: Cementitious Wood Fiber.
System Type E: Membrane mechanically attached to deck.

All General and System Limitations apply. Roof accessories not listed in Table 1 of this NOA are not approved and shall not be installed unless said accessories demonstrate compliance with prescriptive Florida Building Code requirements and are field fabricated utilizing the approved membranes listed in Table 1.

Vapor Barrier: Any UL or FM approved vapor barrier applied to the roof deck.
(Optional)

Fire Barrier: ¼" or ½" DensDeck applied to the deck.
(Optional)

Membrane: FiberTite, FiberTite-XT, FiberTite-SM, FiberTite-XTreme, Style 80 or Style 80-M roof cover attached to the deck following the fastening method specified below:

Fastening: Fasten with Polymer GypTec fasteners and plates spaced 6" o.c. through the fastening tabs spaced 51" o.c. Laps are sealed with 1.5-inch heat weld.

Maximum Design Pressure: -45 psf (See General Limitation #9)



GENERAL LIMITATIONS:

1. Fire classification is not part of this acceptance, refer to a current Approved Roofing Materials Directory for fire ratings of this product.
2. Insulation may be installed in multiple layers. The first layer shall be attached in compliance with Product Control Approval guidelines. All other layers shall be adhered in a full mopping of approved asphalt applied within the EVT range and at a rate of 20-40 lbs./sq., or mechanically attached using the fastening pattern of the top layer
3. All standard panel sizes are acceptable for mechanical attachment. When applied in approved asphalt, panel size shall be 4' x 4' maximum.
4. An overlay and/or recovery board insulation panel is required on all applications over closed cell foam insulations when the base sheet is fully mopped. If no recovery board is used the base sheet shall be applied using spot mopping with approved asphalt, 12" diameter circles, 24" o.c.; or strip mopped 8" ribbons in three rows, one at each sidelap and one down the center of the sheet allowing a continuous area of ventilation. Encircling of the strips is not acceptable. A 6" break shall be placed every 12' in each ribbon to allow cross ventilation. Asphalt application of either system shall be at a minimum rate of 12 lbs./sq. **Note: Spot attached systems shall be limited to a maximum design pressure of -45 psf.**
5. Fastener spacing for insulation attachment is based on a Minimum Characteristic Force (F') value of 275 lbf., as tested in compliance with Testing Application Standard TAS 105. If the fastener value, as field-tested, are below 275 lbf. insulation attachment shall not be acceptable.
6. Fastener spacing for mechanical attachment of anchor/base sheet or membrane attachment is based on a minimum fastener resistance value in conjunction with the maximum design value listed within a specific system. Should the fastener resistance be less than that required, as determined by the Building Official, a revised fastener spacing, prepared, signed and sealed by a Florida Registered Engineer, Architect, or Registered Roof Consultant may be submitted. Said revised fastener spacing shall utilize the withdrawal resistance value taken from Testing Application Standards TAS 105 and calculations in compliance with Roofing Application Standard RAS 117.
7. Perimeter and corner areas shall comply with the enhanced uplift pressure requirements of these areas. Fastener densities shall be increased for both insulation and base sheet as calculated in compliance with Roofing Application Standard RAS 117 and/or RAS 137. Calculations prepared, signed and sealed by a Florida registered Professional Engineer, Registered Architect, or Registered Roof Consultant **(When this limitation is specifically referred within this NOA, General Limitation #9 will not be applicable.)**
8. All attachment and sizing of perimeter nailers, metal profile, and/or flashing termination designs shall conform with Roofing Application Standard RAS 111 and applicable wind load requirements.
9. The maximum designed pressure limitation listed shall be applicable to all roof pressure zones (i.e. field, perimeters, and corners). Neither rational analysis, nor extrapolation shall be permitted for enhanced fastening at enhanced pressure zones (i.e. perimeters, extended corners and corners). **(When this limitation is specifically referred within this NOA, General Limitation #7 will not be applicable.)**
10. All products listed herein shall have a quality assurance audit in accordance with the Florida Building Code and Rule 9N-3 of the Florida Administrative Code.

END OF THIS ACCEPTANCE

